



Via Oberdan, 7 – 20059 Vimercate (MI)  
Tel. : +39 039 6612297  
Fax : +39 039 6612297  
E-mail: [info@fiortech.com](mailto:info@fiortech.com)  
P.I.: 02916370139

## **Description**

RT370 is a highly flame retarded epoxy resin system with excellent physical properties.

## **Benefits**

- Flame retardant compound with low smoke emission
- Excellent potting and encapsulation system with good flow properties
- Excellent electrical properties
- Good chemical resistance to solvents, oils, fuels, acids and bases
- Excellent mechanical and physical properties
- Available in easy-to-use TwinPacks or bulk

## **Typical Properties**

### **Curing (250g mass)**

Work life at 23°C:	2 hours
Cure time at 23°C:	24 hours
Cure time at 80°C:	2 hours

### **Typical Performance (measurements at 23°C)**

Mixed viscosity	250 Pa s
Density	1.6
Shore Hardness	>50 D
Tensile Strength	50 Mpa
Electric Strength	15 kV/mm
Volume Resistivity	10 <sup>11</sup> ohm/cm
Dielectric constant	4
Shrinkage on cure	<1.5%
Operating Temperature	-55°C to 115°C
Flammability (meets requirements)	UL94 V0

## **Colour**

Black

Issue 6 - May 2006

Fiortech warrants only that its products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for its intended use. Fiortech cannot accept any responsibility for loss or damage that may result from the use of this information.

Web site: [www.fiortech.com](http://www.fiortech.com)