



Via Oberdan, 7 – 20059 Vimercate (MI)
Tel. : +39 039 6612297
Fax : +39 039 6612297
E-mail: info@fiortech.com
P.I.: 02916370139

Description

RT371 is a medium viscosity epoxy resin potting system with excellent physical and mechanical properties.

Benefits

- Flame retardant compound with low smoke emission
- Excellent potting and encapsulation system with good flow properties
- Excellent electrical properties
- Good chemical resistance to solvents, oils, fuels, acids and bases
- Excellent mechanical and physical properties
- Available in easy-to-use TwinPacks or bulk

Typical Properties

Curing (250g mass)

Work life at 23 °C:	4 hours
Cure time at 23 °C:	24 hours
Cure time at 80 °C:	4 hours (+ 1 hour @ 120°C for maximum HDT)
Cure time at 120 °C:	2 hours

Typical Performance (measurements at 23°C)

Mixed viscosity	25 Pa s
Density	1.5
Shore Hardness	85 D
Tensile Strength	60 MPa
Electric Strength	>20 Kv/m
Volume Resistivity	10 ¹¹ ohm/cm
Dielectric constant	4
Heat Distortion Temperature	95 °C
Shrinkage on cure	<1.5%
Operating Temperature	-55 °C to 150 °C
Flammability (meets requirements)	UL94 V0

Colour

Blue

Issue 4 - April 2005

Fiortech warrants only that its products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for its intended use. Fiortech cannot accept any responsibility for loss or damage that may result from the use of this information.

Web site: www.fiortech.com